

25

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
5 December 2002 (05.12.2002)

PCT

(10) International Publication Number
WO 02/096843 A1

- (51) International Patent Classification⁷: C07C 11/02, 5/25, 11/08
- (21) International Application Number: PCT/US02/16097
- (22) International Filing Date: 22 May 2002 (22.05.2002)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
09/863,973 23 May 2001 (23.05.2001) US
- (71) Applicant: ABB LUMMUS GLOBAL INC. [US/US];
1515 Broad Street, Bloomfield, NJ 07003 (US).
- (72) Inventors: GARTSIDE, Robert, J.; 167 Colonial Road,
Summit, NJ 07901 (US). GREENE, Marvin, I.; 19 Cam-
bridge Place, Wayne, NJ 07470 (US).
- (74) Agents: CALDERONE, Adrian, T. et al.; Dilworth &
Barrese, LLP, 333 Earle Ovington Blvd., Uniondale, NY
11553 (US).
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG,
SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VN,
YU, ZA, ZM, ZW.
- (84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR,
GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent
(BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR,
NE, SN, TD, TG).
- Published:**
— with international search report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: OLEFIN ISOMERIZATION PROCESS

(57) Abstract: An olefin isomerization process employs a basic metal oxide catalyst, such as magnesium oxide. The catalyst is preferably a high purity magnesium oxide. The olefin isomerization process and catalyst described herein are advantageously used for the production of a terminal olefin such as 1-butene from an internal olefin such as 2-butene.

WO 02/096843 A1

OLEFIN ISOMERIZATION PROCESS

5 BACKGROUND OF THE INVENTION1. Field of the Invention

The present invention relates to an olefin isomerization process employing a basic metal oxide catalyst and to the composition of the catalyst to improve its active life.

10 2. Description of the Related Art

There is a growing need for terminal (alpha) olefins such as 1-butene or 1-hexene. The commercial production of alpha olefins is usually accomplished by the isolation of the alpha
15 olefin from a hydrocarbon stream containing a relatively high concentration of the 1-isomer. For example, 1-butene can be isolated from the C₄ product of steam cracking. Steam cracking C₄ streams contain not only the 1-butene stream but also 2-butene, isobutylene, butadiene and both normal and iso
20 butanes. The 1-butene is isolated by first separating butadiene by extractive distillation or removing butadiene by hydrogenation. Isobutylene can be removed either by reaction (e.g. reaction with methanol to form MTBE), or by
25 fractionation, with the remaining n-butenes being separated by distillation into a 1-butene overhead stream and a 2-butene bottom product. An alternate production method for alpha

olefins involves the dimerization of ethylene to form 1-butene or the trimerization of ethylene to form 1-hexene. Other methods include molecular sieve adsorption of the linear olefins (used for low concentrations).

5 Another process for providing alpha olefins is catalytic isomerization from internal olefins, which accomplishes the shifting of the double bond in an olefin molecule from, for example, an internal position (2-butene) to a terminal position (1-butene). High temperatures favor the
10 isomerization of internal olefin to the alpha olefin. However, high temperature tends to cause catalyst coking which shortens catalyst life. The duration of catalyst activity is a significant factor with respect to the economic viability of a process. The more often a process has to be interrupted for
15 catalyst regeneration the more costly the process becomes. Hence, a method for maintaining peak catalyst activity over a longer period of time at high temperature is a significant advantage for olefin isomerization.

20 SUMMARY OF THE INVENTION

 An olefin isomerization process is provided herein which comprises contacting a fluid feed stream containing an olefin with an activated basic metal oxide catalyst under olefin isomerization conditions, the activated catalyst having an
25 initial activity for olefin isomerization and containing an amount of activity-affecting impurity which does not exceed

that amount which will result in a reduction of the initial catalyst activity at a rate of 0.075 percent conversion loss/hr as measured by the isomerization conversion of 1-butene to 2-butene.

5 The invention herein advantageously provides a basic oxide isomerization catalyst possessing an extended period of catalyst activity at relatively high isomerization temperatures. The isomerization process is advantageously used for the isomerization of internal olefins such as 2-
10 butene or 2-hexene to terminal olefins such as 1-butene or 1-hexene.

BRIEF DESCRIPTION OF THE DRAWINGS

Various embodiments of the invention are described herein
15 with reference to the drawings wherein:

FIG. 1 is a schematic flow diagram of a method for treating a mixture of C₄ compounds from a cracker;

FIG. 2 is a schematic flow diagram of the olefin isomerization process of the present invention;

20 FIGS. 3 and 4 are charts illustrating the 1-butene olefin isomerization conversion vs. time achieved by magnesium oxide catalyst of the present invention; and,

FIGS. 5 and 6 are charts illustrating the 1-butene olefin isomerization conversion vs. time achieved by conventional
25 magnesium oxide catalyst.

DETAILED DESCRIPTION OF PREFERRED EMBODIMENT(S)

The olefin isomerization method herein is directed to the conversion of internally olefinic compounds to terminally olefinic compounds. While the method is described below particularly with reference to the conversion of 2-butene to 1-butene, the conversion of any internally olefinic compound to the terminally olefinic isomer is encompassed within the scope of the invention. Thus, for example, the conversion of 2-pentene to 1-pentene, 2-hexene or 3-hexene to 1-hexene, 2-heptene or 3-heptene to 1-heptene, and the like are also contemplated.

In a typical olefins plant, saturated hydrocarbons are converted to a mixture of olefins by a cracking process such as thermal cracking, steam cracking, fluid catalytic cracking and the like.

The resultant effluent from that cracking reaction is separated into carbon number fractions using a series of distillation columns and refrigerated heat exchange. In one sequence, a demethanizer is used for the removal of methane and hydrogen followed by a deethanizer for the removal of ethane, ethylene, and C_2 acetylene. The bottoms from this deethanizer tower consist of a mixture of compounds ranging in carbon number from C_3 to C_6 . This mixture is separated into different carbon numbers, typically by fractionation.

The C_3 cut, primarily propylene, is removed as product and is ultimately used for the production of polypropylene or as a

feedstock for synthesis of cumene or propylene oxide or acrylonitrile or other important chemical intermediates. The methyl acetylene and propadiene (MAPD) impurities must be removed either by fractionation or hydrogenation.

5 Hydrogenation is preferred since some of these highly unsaturated C₃ compounds end up as propylene thereby increasing the yield.

The C₄ cut consisting of C₄ acetylenes, butadiene, iso and normal butenes, and iso and normal butane can be processed in many ways. A typical steam cracker C₄ cut contains components as set forth in Table 1. Table 1 is given for purposes of exemplification only. Component percentages of C₄ streams can be outside of the ranges given in Table 1.

15 TABLE 1

C ₄ acetylenes	trace
butadiene	30-40 wt. percent
1-butene	10-20 wt. percent
2-butene	5-15 wt. percent
20 isobutene	20-40 wt. percent
iso & normal butane	5-15 wt. percent

25 In a preferred method the processing of the C₄ stream is diagrammatically illustrated in FIG. 1. A stream 10 containing a mixture of C₄ components is sent to a catalytic distillation/ hydrogenation unit 11 for hydrogenating the C₄-acetylenes and the butadiene to 1-butene and 2-butene.

30 Hydrogenation can be performed in a conventional manner in a fixed bed or alternately in a catalytic distillation unit. The

catalytic hydrogenation unit 11 can employ any suitable hydrogenation catalyst such as, for example, palladium on alumina, in a packed bed. Hydrogen can be added at a level representing 1.0 to 1.5 times the hydrogen required to hydrogenate the dienes and acetylenes to olefins. The conditions are variable depending on reactor design. If, for example, the catalytic hydrogenation unit 11 is operated as a catalytic distillation unit, the temperature and pressure are consistent with fractionation conditions. The C₄ fraction 12 produced by catalytic hydrogenation unit 11 contains mainly 1-butene, 2-butene, isobutene and a small amount of other components such as normal and iso butanes.

Under such conditions of hydrogenation, hydroisomerization reactions also occur. Significant quantities of 2-butene are formed by the hydroisomerization of 1-butene, which is produced by the hydrogenation of butadiene.

The fraction 12, now containing only olefins and paraffins, is processed for the removal of the isobutylene fraction in unit 13. There are a number of processes that will accomplish this.

In a preferred method the isobutene is removed by catalytic distillation combining hydroisomerization and superfractionation in unit 13. The hydroisomerization converts 1-butene to 2-butene, and the superfractionation removes the isobutene in stream 14, leaving a relatively pure 2-butene stream 15 containing some n-butane. The advantage to

converting the 1-butene to 2-butene in this system is that the boiling point of 2-butene (1°C for the trans isomer, 4°C for the cis isomer) is further away from the boiling point of isobutylene (-7°C) than that of 1-butene (-6°C), thereby rendering the removal of isobutene by superfractionation easier and less costly and avoiding the loss of 1-butane overhead with the isobutylene. The relatively pure 2-butene stream 15 is used as a feed stream F for the olefin isomerization process described below.

Alternately, unit 13 (isobutylene removal) could be an MTBE unit where isobutylene is removed via reaction with methanol to form MTBE. The remaining normal olefins (stream 15) consisting of 1 and 2-butenes, are relatively untouched in this reaction.

Referring now to FIG. 2, the isomerization of a feed F containing primarily 2-butene by the system 20 is illustrated. Feed F is mixed with a 2-butene recycle stream R and is sent to a first heat exchanger 21 wherein heat is recovered from the effluent stream 24 of the isomerization reactor 23. Feed F is then sent to a heater 22 which raises the temperature of the feed stream to a preferred isomerization temperature of at least about 250°C, preferably from about 300°C to about 600°C, more preferably from about 340°C to about 500°C. Feed F then enters isomerization reactor 23 where it is contacted with an isomerization catalyst, such as described below, at the isomerization temperature. Reaction pressure is not

critically important and can range from subatmospheric to more than 400 psig. Reactor 23 can be any reactor suitable for isomerization such as axial flow, radial flow or parallel flow. The catalyst can be in the form of particulate such as powder, pellets, extrudate, etc.

As stated above, higher temperatures shift the reaction equilibrium to favor the production of 1-butene. At the isomerization temperatures indicated above, a 2-butene conversion of 20 percent to 30 percent to 1-butene is achievable.

The effluent 24 is passed through heat exchanger 21, for heat recovery and is then sent to a fractionator 25 for separation of the 1-butene and 2-butene isomers. Condenser 26 recycles 1-butene for reflux. A relatively pure 1-butene stream is drawn off as overhead product P. A bottoms fraction B containing unreacted 2-butene and butanes is produced. A portion of the 2-butene rich bottoms is sent via recycle stream R back to the feed F. A small portion of the bottoms fraction is bled off at stream 28. Since the feed F contains some butanes, which are unreacted and are separated with the fractionator bottoms, the butanes would accumulate through recycling, thereby wasting energy if the bottoms were not bled. One skilled in the art would adjust the amount of bottoms bled off stream 28 and recycled via stream R to achieve the most economical operation of the system.

Useful isomerization catalysts include basic metal oxides such as magnesium oxide, calcium oxide, barium oxide, and lithium oxide, either individually or in combination. Other oxides such as sodium oxide or potassium oxide can be incorporated into the catalyst as promoters. The preferred catalyst for use in the isomerization method described herein is magnesium oxide (MgO) and the invention will be described in terms of magnesium oxide, although it should be understood that the other basic metal oxides mentioned above are also contemplated as being within the scope of the invention. The magnesium oxide catalyst can be in the form of powder, pellets, extrudates, and the like.

One of the problems associated with magnesium oxide and other basic oxide catalysts is the shortness of the duration of its catalytic activity under favorable isomerization conditions of high temperature to form the alpha olefin. Conventional magnesium oxide (or other basic metal oxide) catalyst experiences a rapid drop of catalyst activity after about 20-40 hours of operation on-stream. The deactivation rates as measured by the loss of conversion of 1-butene to 2-butene are approximately 0.3 percent conversion loss/hr or higher. Such a rapid loss of initial activity either as a fresh catalyst or regenerated catalyst renders the process economically less feasible and inhibits the wider use of magnesium oxide as an isomerization catalyst.

Typically, the catalyst is treated in dry inert gas to remove residual water and carbon dioxide prior to use in the isomerization reaction. Water and carbon dioxide are generally chemically bound to the magnesium oxide in the form of magnesium hydroxide and magnesium carbonate. Although not wishing to be bound by any explanation, it is believed that these compounds act as acid sites which promote the fouling reactions that limit the onstream cycle life of the system.

A significant feature of the basic oxide catalyst used in the present method is its purity. Certain impurities adversely affect the activity of the basic metal oxide catalyst. Activity-affecting impurities such as sulfur or phosphorous (usually in the form of compounds such as sulfides, sulphates, phosphates, and the like) can form highly acidic oxides which lead to undesirable cracking reactions which foul the catalyst and limit the cycle life at desirable isomerization conditions. Likewise, activity-affecting impurities such as transition metals (e.g., iron, chromium, cobalt and nickel in their oxide form) are believed to act as catalysts for various cracking and dehydrogenation reactions which lead to coke formation and also limit the cycle life of the catalyst at desirable isomerization conditions. The amount of activity-affecting impurity should be as small as possible. Preferably, the amount of activity-affecting impurity in the catalyst does not exceed that amount which would result in a reduction of the initial catalyst activity

at a rate of not more than about 0.075 percent conversion loss/hr as measured by the isomerization of 1-butene to 2-butene, preferably not more than about 0.050 percent conversion loss/hr, and more preferably not more than about 0.035 percent conversion loss/hr. The 0.075% conversion loss/hr translates into an equivalent of a 1 week cycle length defined by an approximate 15 percent loss in 1-butene conversion over the time period.

Accordingly, the basic metal oxide catalyst of the present invention contains, in parts by weight, no more than about 2000 ppm of sulfur and/or phosphorous, and no more than about 500 ppm of transition metal, preferably no more than about 1000 ppm of sulfur and/or phosphorous and no more than about 400 ppm of transition metal, and most preferably no more than about 75 ppm of sulfur and/or phosphorous and no more than about 330 ppm of transition metals.

While the adverse affect on catalyst life caused by water and carbon dioxide can be reversed under activation or regeneration temperatures, the acid sites caused by sulfur, phosphorous, or transition metals are not easily removed. Accordingly, it is important that the basic metal oxide initially be of high purity. High purity basic metal oxides can be prepared by one skilled in the art or can be obtained commercially.

Table 2 below sets forth a comparison of the impurity levels of a preferred high purity magnesium oxide catalyst and a conventional magnesium oxide catalyst.

TABLE 2

	<u>Impurity</u>	<u>High purity MgO Impurity level (ppm)</u>	<u>Conventional grade MgO Impurity level (ppm)</u>
10	Iron	330	692
	Sulfur	74	2335
15	Calcium	4100	3522
	Sodium	2250	2250

Prior to its initial use in an olefin isomerization reaction the magnesium oxide (or other basic metal oxide catalyst) is heated in a dry inert atmosphere at sufficiently high temperature to remove substantially all activity-affecting amounts of water and carbon dioxide. A suitable initial activation treatment of the magnesium oxide catalyst can be performed in one or more steps. Preferably, a two step process is employed wherein the magnesium oxide catalyst is first preheated for at least about 15 hours at a temperature of least 350°C in a dry inert atmosphere as a drying first step. More particularly, a flow of dry pure inert gas such as nitrogen is passed through a bed of magnesium oxide catalyst at a temperature of at least about 350° C for at least about 15 hours while the effluent is monitored for release of water

and carbon dioxide. The effluent water concentration is brought down to less than 1 ppm.

In a preferred second step the catalyst is activated by contact with an inert gas (e.g., nitrogen) at about at least 500°C, preferably at about at least 550°C for at least about 6 hours. This removes even more CO₂ and H₂O.

While the initial treatment method described above improves the catalyst performance enabling operation of the isomerization for a period of over 150 hours, the olefin isomerization process must be cycled to allow for regeneration of the catalyst to remove coke deposits. The benefit of the dry-out achieved by the treatment method set forth above is lost on the second cycle when standard regeneration procedures are employed.

The regeneration method herein restores the catalyst to substantially its initial fresh condition and includes a decoking step, preferably followed by a high temperature catalyst reactivation step.

The decoking step substantially completely removes all activity affecting amounts of coke. In the decoking process however, water and carbon dioxide, which are both products of combustion, are deposited on the catalyst surface. The high temperature reactivation step removes substantially any remaining traces of water and/or carbon dioxide capable of affecting catalyst activity for further extension of catalyst life and restores the catalyst to substantially its initial

level of activity. More particularly, the decoking step includes contacting the catalyst with a flowing atmosphere containing a dry inert gas (e.g., nitrogen) and an oxidizing agent (e.g., oxygen) at a final regeneration temperature of at least about 500°C for at least about 18 hours to substantially completely remove all coke from the catalyst. The regeneration proceeds in steps of gradually increasing temperature and oxygen concentration as described in U.S. Patent No. 4,217,244, which is herein incorporated by reference. In the final step, the catalyst is exposed to high levels of oxygen. Pure, dry air with at least about 20 volume percent oxygen is preferably used as the flowing atmosphere. Following the oxidation step, the catalyst is exposed to the procedure for reactivation as used prior to initial operation. A two step nitrogen dryout to remove the products of combustion is utilized.

A preferred activation method for the olefin isomerization catalyst is disclosed and described in U.S. Patent application Serial No. _____ filed concurrently herewith (under Attorney Docket No. 1094-10), which is herein incorporated by reference.

Various aspects of the invention are illustrated by the Examples and Comparative Examples given below:

Example 1

A sample of high purity magnesium oxide (hereinafter designated as Sample A) was provided, the sample containing 330 ppm iron, 74 ppm sulfur, 4100 ppm calcium and less than 250 ppm sodium.

5 Sample A was treated according to the initial dryout procedures referenced above. Sample A was then operated in 1-butene isomerization conditions and was coked until substantially all catalyst activity was lost. After a nitrogen flush, the sample was exposed to a regeneration
10 procedure consisting of a programmed increase in temperature and oxygen concentration with a final step of exposure to nitrogen containing 21 percent oxygen for 18 hours at 500°C. Thereafter, a high temperature reactivation step was performed on the sample by exposing the sample to dry nitrogen at 550°C.
15 The sample was treated with nitrogen containing approximately 10 ppm of oxygen.

Sample A was then individually tested in an isomerization of 1-butene to 2-butene for catalyst activity. The isomerization reaction was conducted at 450 psig, 515°F and 27
20 WHSV. The feed stream included 65 percent diluent. The catalyst activity was measured in terms of the 1-butene conversion in mol percent.

The results of this test are tabulated in Table 3 and graphically illustrated in FIG. 3. As can be seen the overall
25 deactivation rate of Sample A was 0.033 percent conversion lost per hour.

Example 2

A sample of high purity magnesium oxide (hereinafter designated as Sample B) was provided, the sample containing 330 ppm iron, 74 ppm sulfur, 4100 ppm calcium and less than 250 ppm sodium.

Sample B was treated according to the same procedures as set forth above in Example 1.

Sample B was then individually tested in an isomerization of 1-butene for catalyst activity. The isomerization reaction was conducted at 450 psig, 520°F and 26.6 WHSV. The feed stream included 65 percent diluent. The catalyst activity was measured in terms of the 1-butene conversion in mol percent.

The results of this test are tabulated in Table 3 and graphically illustrated in FIG. 4. As can be seen the overall deactivation rate of Sample B was 0.027 percent conversion lost per hour.

Comparative Example 1

A sample of conventional grade magnesium oxide (hereinafter designated as Sample C) was provided, the sample containing 692 ppm iron, 2335 ppm sulfur, 3522 ppm calcium and less than 250 ppm sodium.

Sample C was treated according to the same procedures as set forth above in Example 1.

Sample C was then individually tested in an isomerization of 1-butene for catalyst activity. The isomerization reaction

was conducted at 450 psig, 519°F and 27 WHSV. The feed stream included 65 percent diluent. The catalyst activity was measured in terms of the 1-butene conversion in mol percent.

The results of this test are tabulated in Table 3 and graphically illustrated in FIG. 5. As can be seen the overall deactivation rate of Sample C was 0.281 percent conversion lost per hour.

Comparative Example 2

A sample of conventional grade magnesium oxide (hereinafter designated as Sample D) was provided, the sample containing 692 ppm iron, 2335 ppm sulfur, 3522 ppm calcium and less than 250 ppm sodium.

Sample D was treated according to the same procedures as set forth above in Example 1.

Sample D was then individually tested in an isomerization of 1-butene for catalyst activity. The isomerization reaction was conducted at 76 psig, 517°F and 9 WHSV. The feed stream included 65 percent diluent. The catalyst activity was measured in terms of the 1-butene conversion in mol percent.

The results of this test are tabulated in Table 3 and graphically illustrated in FIG. 6. As can be seen the overall deactivation rate of Sample D was 0.373 percent conversion lost per hour. Increasing the amount of catalyst by a factor of 3 (i.e., a WHSV of 9 as opposed to a WHSV of 27) did not

materially change the rate of conversion loss for the entire system.

These results show that conventional grade magnesium oxide olefin catalysts experience a loss of olefin conversion activity which is about 10 times greater than the high purity magnesium oxide catalysts of the present invention under desirable olefin isomerization conditions. Moreover, the high purity catalyst exhibited a higher initial conversion to 2-butene.

TABLE 3

Sample	A - High Purity MgO	B - High Purity MgO	C - Commercial MgO	D - Commercial MgO
Initial 1-C ₄ Conversion, mol%	83.1	82.4	80.4	77.0
Final 1-C ₄ Conversion mol%/hours	80.5% / 80	78.0% / 148	70.0 / 40	53.5/72
Deactivation Rate % lost/hr	0.033	0.027	0.281	0.373
Pressure	450 psig	450 psig	450 psig	76 psig
Temperature	515° F	520° F	519° F	517° F
WHSV, lb/lb/hr	27	26.6	27	9

It will be understood that various modifications may be made to the embodiments described herein. Therefore, while the above description contains many specifics, these specifics should not be construed as limitations on the scope of the invention, but merely as exemplifications of preferred embodiments thereof. Those skilled in the art will envision

many other possible variations that are within the scope and spirit of the invention as defined by the claims appended hereto.

What is claimed is:

1. An olefin isomerization process which comprises contacting a fluid feed stream containing an olefin with an activated basic metal oxide catalyst under olefin isomerization conditions, the activated catalyst having an initial activity for olefin isomerization and containing an amount of activity-affecting impurity which does not exceed that amount which will result in a reduction of the initial catalyst activity by about 0.075 percent conversion loss per hour as measured by the isomerization of 1-butene to 2-butene.

2. The olefin isomerization process of claim 1 wherein the basic metal oxide catalyst is selected from the group consisting of magnesium oxide, calcium oxide, barium oxide, lithium oxide and combinations thereof.

3. The olefin isomerization process of claim 1 wherein the catalyst is magnesium oxide.

4. The olefin isomerization process of claim 1 wherein the activity-affecting impurity in the basic metal oxide catalyst is, or contains, sulfur, phosphorus, at least one transition metal or a combination thereof.

5. The olefin isomerization process of claim 4 wherein the at least one transition metal is iron, chromium, cobalt, nickel, or a combination thereof.

5 6. The olefin isomerization process of claim 1 wherein the catalyst contains no more than about 2000 ppm of sulfur and/or phosphorous and no more than about 500 ppm of one or more transition metals.

10 7. The olefin isomerization process of claim 1 wherein the catalyst contains no more than about 1000 ppm of sulfur and/or phosphorous and no more than about 400 ppm of one or more transition metals.

15 8. The olefin isomerization process of claim 1 wherein the catalyst contains no more than about 75 ppm of sulfur and/or phosphorous and no more than about 330 ppm of one or more transition metals.

20 9. The olefin isomerization process of claim 1 wherein the fluid feed stream comprises an olefin possessing an internal double bond, at least some of the olefin possessing an internal double bond being converted to a corresponding terminal olefin.

25

10. The olefin isomerization process of claim 9 wherein the olefin possessing an internal bond comprises 2-hexene and/or 3-hexene and the corresponding terminal olefin is 1-hexene.

5

11. The olefin isomerization process of claim 9 wherein the olefin possessing an internal double bond is 2-butene and the corresponding terminal olefin is 1-butene.

10

12. The olefin isomerization process of claim 10 wherein the conversion of 2-butene to 1-butene is from about 20 percent to about 30 percent.

15

13. The olefin isomerization process of claim 1 wherein the olefin isomerization conditions include a temperature of at least about 300°C.

20

14. The olefin isomerization process of claim 1 wherein the olefin isomerization conditions include a temperature of from about 340°C to about 500°C.

25

15. The olefin isomerization process of claim 1 wherein the basic metal oxide catalyst is selected from the group consisting of magnesium oxide, calcium oxide, barium oxide, lithium oxide and combinations thereof, and the activity-

affecting impurity includes sulfur, phosphorus, at least one transition metal or a combination thereof.

16. The olefin isomerization process of claim 15 wherein
5 the at least one transition metal is iron, chromium, cobalt,
nickel, or a combination thereof.

17. The olefin isomerization process of claim 3 wherein
the catalyst contains no more than about 2000 ppm of sulfur
10 and/or phosphorous and no more than about 500 ppm of one or
more transition metals.

18. The olefin isomerization process of claim 3 wherein
the catalyst contains no more than about 1000 ppm of sulfur
15 and/or phosphorous and no more than about 400 ppm of one or
more transition metals.

19. The olefin isomerization process of claim 3 wherein
the catalyst contains no more than about 75 ppm of sulfur
20 and/or phosphorous and no more than about 330 ppm of one or
more transition metals.

20. A process for isomerizing C₄ olefin derived from a
mixed C₄ stream comprising the steps of:

25 a) providing a C₄ stream containing butadiene, 1-butene,
2-butene, and isobutylene;

b) selectively hydrogenating the C₄ stream in the presence of a hydrogenation catalyst and hydrogen whereby the butadiene is selectively hydrogenated;

5 c) simultaneously hydroisomerizing and fractionating the feed to convert 1-butene to 2-butene and to remove the isobutylene by fractionation; and

d) contacting the C₄ stream with an activated basic metal oxide catalyst under olefin isomerization conditions, the activated catalyst having an initial activity for olefin
10 isomerization and containing an amount of activity-affecting impurity which does not exceed that amount which will result in a reduction of the initial catalyst activity by about 0.075 percent conversion loss per hour.

15 21. The process of claim 20 wherein the basic metal oxide catalyst contains no more than about 2000 ppm of sulfur and/or phosphorous and no more than about 500 ppm of one or more transition metals.

20 22. The process of claim 20 wherein the basic metal oxide catalyst contains no more than about 1000 ppm of sulfur and/or phosphorous and no more than about 400 ppm of one or more transition metals.

25 23. The process of claim 20 wherein the basic metal oxide catalyst contains no more than about 75 ppm of sulfur and/or

phosphorous and no more than about 330 ppm of one or more transition metals.

1/6





FIG 1

2/6

**FIG 2**

3/6






FIG 3

4/6

**FIG. 4**

5/6

**FIG 5**

6/6




FIG 6

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 02/16097

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C07C11/02 C07C5/25 C07C11/08

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C07C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 00 09261 A (KANSAS STATE UNIVERSITY RESEARCH FOUNDATION) 24 February 2000 (2000-02-24) example 4	1-3, 15
A	US 3 169 987 A (BLOCH HERMAN S) 16 February 1965 (1965-02-16) claim 6	1, 2
A	US 1 914 674 A (FRANZ RUNGE ET AL) 20 June 1933 (1933-06-20) claim 6	1, 2

☐ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *8* document member of the same patent family

Date of the actual completion of the international search

19 August 2002

Date of mailing of the international search report

28/08/2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Van Geyt, J

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US 02/16097

Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:

2. ☒ Claims Nos.: 1-5, 9-11, 13-16, 20 (in part); 12 (completely)
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:
see FURTHER INFORMATION sheet PCT/ISA/210

3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

1. ☐ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.

2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.

3. ☐ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:

4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☐ No protest accompanied the payment of additional search fees.

INTERNATIONAL SEARCH REPORT

International Application No. PCT/US 02 16097

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

Continuation of Box I.2

Claims Nos.: 1-5, 9-11, 13-16, 20 (in part); 12 (completely)

Present claims 1, 12 and 20 relate to a process defined by reference to a desirable characteristic or property, namely the reduction of the initial catalyst activity of 0.075 % conversion loss per hour (claims 1 and 20) and the conversion of 2-butene to 1-butene of from 20 to 30% (claim 12). The claims cover all processes having this characteristic or property, whereas the application provides support within the meaning of Article 6 PCT and/or disclosure within the meaning of Article 5 PCT for only a very limited number of such processes. In the present case, the claims so lack support, and the application so lacks disclosure, that a meaningful search over the whole of the claimed scope is impossible. Independent of the above reasoning, the claims also lack clarity (Article 6 PCT). An attempt is made to define the process by reference to a result to be achieved. Again, this lack of clarity in the present case is such as to render a meaningful search over the whole of the claimed scope impossible. Consequently, the search has been carried out for those parts of the claims which appear to be clear, supported and disclosed, namely those parts relating to the processes in which a catalyst containing the impurities as defined in claim 6 or claim 21 is used, regardless of the obtained conversion.

The applicant's attention is drawn to the fact that claims, or parts of claims, relating to inventions in respect of which no international search report has been established need not be the subject of an international preliminary examination (Rule 66.1(e) PCT). The applicant is advised that the EPO policy when acting as an International Preliminary Examining Authority is normally not to carry out a preliminary examination on matter which has not been searched. This is the case irrespective of whether or not the claims are amended following receipt of the search report or during any Chapter II procedure.

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 02/16097

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 0009261	A	24-02-2000	US 6087294 A	11-07-2000
			AU 5550899 A	06-03-2000
			EP 1113875 A1	11-07-2001
			WO 0009261 A1	24-02-2000
US 3169987	A	16-02-1965	NONE	
US 1914674	A	20-06-1933	NONE	